



## TYPICAL PROPERTIES OF EWF®2500 Glassine

Glassine paper is pure cellulose paper. Using only water and energy, the wood pulp is converted to glassine paper. Glassine has a true environmental conscious, from manufacturing to end use and beyond EWF2500 is environmentally kind.

Properties	Units	Typical Values	Test Method
Basis Weight	#	22	—
	g/m <sup>2</sup>	32.56	
Yield	in <sup>2</sup> /lb	19,630	ISO 534
	m <sup>2</sup> /kg	27.88	
Moisture	%	6 – 8	ISO 287
Transparency	%	81	DIN 53 147
pH Value	—	6 – 8	DIN 53 124
Tensile Strength	MD N/15mm	38	ISO 1924

*Thickness & Yields may vary by +/- 10%*

*All data represents typical values by the methods indicated and should be considered so. The information herein, is to the best of our knowledge, true, and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. No warranty is made or implied.*