

**TYPICAL PROPERTIES OF
2800 Release Liner 28#**

This is an unprinted, machine finished bleached kraft paper.
One side has been coated with a 100% solid silicone release coating.

Properties		Unit	Typical Value	Test Method
Yield		in ² /lb m ² /kg	15,429 21.9	ASTM D4321
Basis Weight		lbs/ream g/m ²	28 31.44	ASTM D646
Caliper		mils µm	2.10 52.5	TAPPI T411
Release Value (Silicone)	AA	gr/in	100	TAPPI T5
Tensile Strength	MD CD	lbs/in	12 5	ASTM D828
Tear Strength	MD CD	g	20.0 25.0	TAPPI T414

Thickness & Yields may vary by +/- 10%

All data represents typical values by the methods indicated and should be considered so. The information herein, is to the best of our knowledge, true, and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. No warranty is made or implied.