

**TYPICAL PROPERTIES OF  
2800 Release Liner 30#**

This is an unprinted, machine finished bleached kraft paper.  
One side has been coated with a 100% solid silicone release coating.

Properties		Unit	Typical Value	Test Method
Yield		in <sup>2</sup> /lb	13,660	ASTM D4321
		m <sup>2</sup> /kg	19.4	
Basis Weight		lbs/ream	31.6	TAPPI T410
		g/m <sup>2</sup>	46.8	
Caliper		mils	2.10	TAPPI T411
		µm	52.5	
Release Value (Silicone)	Initial	gr/in	5	TKPR-0002 TAPPI UM-502
	Post		23	
Tensile Strength	MD	lbs/in	27	TAPPI T494
Tear Strength	CD	g	27.0	TAPPI T414

*Thickness & Yields may vary by +/- 10%*

*All data represents typical values by the methods indicated and should be considered so. The information herein, is to the best of our knowledge, true, and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. No warranty is made or implied.*