MULTI–PLASTICS

Glassine

Version: RD072024-25

EnviroSafe®

TYPICAL PROPERTIES OF EWF®2500 Glassine

2500 is a pure cellulose paper. Using only water and energy, the wood pulp is converted to glassine paper. Glassine has a true environmental conscious, from manufacturing to end use and beyond **EWF®2500** is environmentally kind.

Properties	Units	Typical Values	Test Method
Basis Weight	# g/m²	22 32.56	—
Yield	in²/lb m²/kg	19,630 27.88	ISO 534
Moisture	%	6 – 8	ISO 287
Transparency	%	81	DIN 53 147
pH Value	—	6 – 8	DIN 53 124
Tensile Strength MD	N/15mm	38	ISO 1924

Thickness & Yields may vary by +/- 10%

All data represents typical values by the methods indicated and should be considered so. The information herein, is to the best of our knowledge, true, and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. No warranty is made or implied.